

Technical Data Sheet

AS-1232 / AS-1232S Bathroom & Sanitary Sealant



Physical Properties

Appearance:

Paste

Odour:

Slight unique odour

Colour:

Translucent

Tack-free time:

15 – 30 min

Application temperature:

-20 °C to 50 °C

Service temperature:

-50 °C to 150 °C

Storage:

Store in a dry and cool place with temperature below 30 °C.

Shelf life:

12 months

Packaging:

Content	Quantity/ carton
75 g tube carded (AS-1232)	144
32 g tube carded (AS-1232S)	144

Description

ALSEAL Bathroom & Sanitary Sealant is a one-component, neutral cure silicone sealant formulated for excellent mildew resistance. It will form a durable and waterproof seal on most common wet area building materials.

Applications

Warm areas with high humidity (bathrooms, toilets, kitchen, etc.). It will bond on most building materials (ceramics, glass, aluminium, plastics, etc.).

Features

- ◆ Mildew resistant (Anti-fungus)
- ◆ Durable
- ◆ Indoor and outdoor use

Technical Data

Curing system	: Oxime
Specific gravity	: 0.99
Tensile at break (JIS K 6249)	: ≥ 0.8 MPa
Elongation at break (JIS K 6249)	: ≥ 250 %

Usage Instructions

1. Surfaces must be clean, dry and free of dirt, grease, oil or water. Puncture tube with cap.
2. Apply product to substrate.
3. If used as adhesive: Press firmly and let it cure for 6 hours before moving it.
4. If used as sealant: Tool within 5 minutes of extrusion.
5. Replace cap after use and store in a cool, dry place.
6. Product can be cleaned with mineral spirit.

Caution

Product releases methylethylketoxime during application and curing. Keep out of reach of children. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Disclaimer

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that



may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.